

Model: SEA SILVER 33,3X100(A) Codes: 100104794 Water absorption: BIII - Revestimiento (10%<=E<=20%)





DIMENSIONAL FEATURES UNE-EN ISO 10545-2				
Thickness	10.5	+/-5%*		
Width	332.8 MM			
Length	1000 MM			
Length and width deviation	Below 0.15%	+/-0.3%*		
Side straightness deviation	Below 0.15%	+/-0.3%*		
Squareness deviation	Below 0.15%	+/-0.3%*		
Surface flatness deviation	Below 0.15%	+/-0.4%*		
*ISO-13006:2018 UNE-EN 14411:2016				

MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11				
Breaking strength	2059 N	>600N*		
Modulus of rupture	29 N/MM2	>=12N/mm2*		
Crazing resistance	Resists 3 cycles			
*ISO-13006:2018 UNE-EN 14411:2016				

## HYGIENIC FEATURES

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

\*ISO-13006:2018 UNE-EN 14411:2016

## SCOPE OF USE

Technical code-1	Use on walls	
	ANTI-SLIP VA	ALUE
	EN 16165: 2022 / AST	TM C1028
Friction (dry)	No Aplica	
Friction (wet)	No Aplica	
Slip resistance (dcof)	No Aplica	
*ISO-13006:2018 UNF-EN 14411:2016		



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

## 100104794 SEA SILVER



PACKING		
Sales units per box	0.999 M2/BOX	
Sales units per pallet	31.968 M2/PAL	
Sales units per unit	0.333 M2/PIECE	



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.