


Model: IMAGE DARK 40X80(A)

Codes: 100202102

Water absorption: Bla - Porcelánico (E<=0.1%)



DIMENSIONAL FEATURES

 UNE-EN ISO 10545-2

Thickness	10.5 MM	+/-5%*
Width	399 MM	
Length	800 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

*ISO-13006:2018 UNE-EN 14411:2016

MECHANICAL FEATURES

 UNE-EN ISO 10545-4-6-7-11

Breaking strength	3118 N	>1300N*
Modulus of rupture	542.857.142.857.143 N/MM2	>=35N/mm2*
Abrasion resistance	PEI 3 / 600v	
Crazing resistance	Resists 3 cycles	

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES

 UNE-EN ISO 10545-13-14:1995

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

*ISO-13006:2018 UNE-EN 14411:2016

SCOPE OF USE

Technical code-1	Use on medium traffic floors	
------------------	------------------------------	--

ANTI-SLIP VALUE

 EN 16165: 2022 / ASTM C1028

Dynamic coefficient of friction	0.34	
Slip resistance (pendulum-wet)	CL1	
Slip resistance (ramp)	<R-9	TONO 22 / ID 1455*
Slip resistance (bare feet)	A	
4s	29	

*ISO-13006:2018 UNE-EN 14411:2016

System Certification



PACKING

Sales units per box	1.28 M2/BOX	
Sales units per pallet	61.44 M2/PAL	
Sales units per unit	0.32 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.
Mosaic tiles must be grouted.
This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.