

Model: NANTES CALIZA ANT. (20MM) 59,6X59,6(A) Codes: 100297830 Water absorption: BIa - Porcelanico (E<=0.1%)



DIMENSIONAL FEATURES UNE-EN ISO 10545-2		
Thickness	20 MM	+/-5%*
Width	596 MM	
Length	596 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
*ISO-13006:2018 UNE-EN 14411:2016		

	MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11	
Breaking strength	16358 N	>1300N*
Modulus of rupture	61.1 N/MM2	>=35N/mm2*
Crazing resistance	Resists 3 cycles	
*ISO-13006:2018 UNE-EN 14411:2016		

HYGIENIC FEATURES	
UNF-FN ISO 10545-13-14:1995	

Chamical	resistance
Cheffilda	resistance

Class "A" for swimming pools and cleaning products B Min.\* (resists attack). Minimum Class "B" for acids and bases 3 Min.\* Stain resistance Class 5. Easy cleaning with water

\*ISO-13006:2018 UNE-EN 14411:2016

## SCOPE OF USE

Technical code-1	Use on heavy traffic floors	
ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028		
Dynamic coefficient of friction	>0,42	
Slip resistance (pendulum-wet)	CL3	
Slip resistance (ramp)	R-11	13866*
*ICO 4200C 2040 UNE EN 44444 204C		

\*ISO-13006:2018 UNE-EN 14411:2016



## 100297830 NANTES CALIZA ANT.

## PORCELANOSA Grupo

	PACKING	
Sales units per box	0.710429 M2/BOX	
Sales units per pallet	22.733731 M2/PAL	
Sales units per unit	0.355215 M2/PIECE	



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.