

Model: TREVISO BEIGE LAP.L 120X120(A) Codes: 100305852 Water absorption: BIa - Porcelanico (E<=0.1%)





DIMENSIONAL FEATURES UNE-EN ISO 10545-2				
Thickness	8.5 MM	+/-5%*		
Width	1200 MM			
Length	1200 MM			
Length and width deviation	Below 0.15%	+/-0.3%*		
Side straightness deviation	Below 0.15%	+/-0.3%*		
Squareness deviation	Below 0.15%	+/-0.3%*		
Surface flatness deviation	Below 0.15%	+/-0.4%*		
*ISO-13006:2018 UNE-EN 14411:2016				

MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11				
Breaking strength	2366 N	>1300N*		
Modulus of rupture	53 N/MM2	>=35N/mm2*		
Abrasion resistance	PEI 4 / 1500v			
Crazing resistance	Resists 3 cycles			
*ISO-13006:2018 UNE-EN 14411:2016				

HYGIENIC FEATURES UNE-EN ISO 10545-13-14:1995		
Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*	
Class 5. Easy cleaning with water	3 Min.*	
	UNE-EN ISO 10545-13-14:1995 Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	

SCOPE OF USE		
Technical code-1	Use on medium traffic floors	
	ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028	
Slip resistance (pendulum-wet)	CLO	
*ISO-13006:2018 UNE-EN 14411:2016		
PACKING		

Sales units per pallet 1.440092 M2/BOX   Sales units per pallet 60.483871 M2/PAL			
	Sales units per box	1.440092 M2/BOX	
	Sales units per pallet	60.483871 M2/PAL	
Sales units per unit 1.440092 M2/PIECE	Sales units per unit	1.440092 M2/PIECE	





Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.