

Model: MORSE COAL NATURE L 29,7X59,6(A) Codes: 100326965 Water absorption: BIa - Porcelanico (E<=0.1%)



Sistema DAPc<sup>®</sup> Declaración Ambiental de Productos de Construcción

	DIMENSIONAL FEATURES UNE-EN ISO 10545-2	
Thickness	8.5 MM	+/-5%*
Nidth	297 MM	
Length	596 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
*ISO-13006:2018 UNE-EN 14411:2016		
	MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11	
Breaking strength	2338.2 N	>1300N*
Modulus of rupture	54.8 N/MM2	>=35N/mm2*
Crazing resistance	Resists 3 cycles	
*ISO-13006:2018 UNE-EN 14411:2016		
	HYGIENIC FEATURES	
	UNE-EN ISO 10545-13-14:1995	
Chemical resistance	Class "A" for swimming pools and cleaning products	B Min.*
	(resists attack). Minimum Class "B" for acids and bases	
Stain resistance	Class 5. Easy cleaning with water	3 Min.*
*ISO-13006:2018 UNE-EN 14411:2016		
	SCOPE OF USE	
Technical code-1	Use on heavy traffic floors	
	ANTI-SLIP VALUE	
	EN 16165: 2022 / ASTM C1028	
Dynamic coefficient of friction	0.52	
Slip resistance (pendulum-wet)	CL1	
*ISO-13006:2018 UNE-EN 14411:2016		
	PACKING	
Salas units par box		
Sales units per box	1.062078 M2/BOX	
Sales units per pallet	50.979767 M2/PAL	
Sales units per unit	0.177013 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.