

Model: THASSOS L 59,6X59,6(A) Codes: 100328007 Water absorption: Blb - Gres (0.5%<E<=3%)



Sistema DAPc® Declaración Ambiental de Broductor de Construcción

DIMENSIONAL FEATURES UNE-EN ISO 10545-2				
Thickness	8.5 MM	+/-5%*		
Width	596 MM			
Length	596 MM			
Length and width deviation	Below 0.15%	+/-0.3%*		
Side straightness deviation	Below 0.15%	+/-0.3%*		
Squareness deviation	Below 0.15%	+/-0.3%*		
Surface flatness deviation	Below 0.15%	+/-0.4%*		
*ISO-13006:2018 UNE-EN 14411:2016				

MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11				
Breaking strength	2265.0 N	>1100N*		
Modulus of rupture	48.15 N/MM2	>=30N/mm2*		
Abrasion resistance	PEI 4 / 1500v			
Crazing resistance	Resists 3 cycles			
*ISO-13006:2018 UNE-EN 14411:2016				

	HYGIENIC FEATURES UNE-EN ISO 10545-13-14:1995	
Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*
*ISO-13006:2018 UNE-EN 14411:2016		

	SCOPE OF USE	
Technical code-1	Use on medium traffic floors	
	ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028	
Slip resistance (pendulum-wet)	CLO	
*ISO-13006:2018 UNE-EN 14411:2016		
PACKING		

Sales units per box 1.776073 M2/BOX Sales units per pallet 56.834328 M2/PAL Sales units per unit 0.255215 M2/UECE	TACKING			
		Sales units per box	1.776073 M2/BOX	
Salas units por unit		Sales units per pallet	56.834328 M2/PAL	
Sales units per unit 0.555215 M2/FIECE		Sales units per unit	0.355215 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.