

Model: NYLO NOIR POL.04 120X270(6)(A) Codes: 100332561 Absorption: Bla - Porcelanico (E<=0.1%)



Sistema DAPc[®] Declaración Ambiental de Productos de Construcción

| | DIMENSIONAL FEATURES UNE-EN ISO 10545-2 | |
|-----------------------------------|--|----------|
| Length | 2700 MM | |
| Thickness | 6 MM | |
| Width | 1200 MM | |
| Length and width deviation | Below 0.15% | +/-0.3%* |
| Side straightness deviation | Below 0.15% | +/-0.3%* |
| Squareness deviation | Below 0.15% | +/-0.3%* |
| Surface flatness deviation | Below 0.15% | +/-0.4%* |
| *ISO-13006:2015 UNE-EN 14411:2017 | | |

| | MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11 | |
|-----------------------------------|--|--|
| Breaking strenght | >1100 N | |
| Modulus of rupture | >45 N/MM2 | |
| Abrasion resistance | <140 | |
| *ISO-13006:2015 UNE-EN 14411:2017 | | |

| | HYGIENIC FEATURES UNE-EN ISO 10545-13-14 | |
|---|---|--|
| Chemical resistance | MIN B | |
| Stain resistance | 5 | |
| Resistance to cold food products | SUITABLE | |
| Resistance to hot food products | SUITABLE | |
| Fastness to rubbing | SUITABLE | |
| Dimensional stability at elevated temperature | COMPLIANT | |
| Climate shock test. resistance index | RESISTS | |
| Resistance to thermal shock | RESISTE | |
| Flammability | A1 | |
| *ISO-13006:2015 UNE-EN 14411:2017 | | |



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

100332561 NYLO NOIR POLISHED 04

PORCELANOSA Grupo

| CEN/TS 41901/02, DIN-51130 y ASTM A137.1 |
|---|
| Slip resistance (pendulum-wet) CL0 |
| Resistance to bacteria SUITABLE |
| Resistance to cleaning products SUITABLE |
| Resistance to bathroom cleaning products SUITABLE |
| Resistance to cigarette burns SUITABLE |
| 4s DRY>36-LOW_WET<25-HIGH |
| Slip resistance (pendulum-dry) >45 |
| *ISO-13006:2015 UNE-EN 14411:2017 |

SCOPE OF USE

Technical code-1 Technical code-2

No additional requirements

Use on walls

| | PACKING |
|------------------------|-------------------|
| Sales units per box | 3.240441 M2/BOX |
| Sales units per pallet | 71.289695 M2/PAL |
| Sales units per unit | 3.240441 M2/PIECE |



ACREDITA

SGS

SGS

SGS

Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.