

Model: GENT ROBLE 19,3X180(A) Codes: 100337240 Water absorption: BIa - Porcelanico (E<=0.1%)



Sistema DAPc<sup>®</sup> Declaración Ambiental de Productos de Construcción

DIMENSIONAL FEATURES UNE-EN ISO 10545-2			
Thickness	11.5 MM	+/-5%*	
Width	193 MM		
Length	1800 MM		
Length and width deviation	Below 0.15%	+/-0.3%*	
Side straightness deviation	Below 0.15%	+/-0.3%*	
Squareness deviation	Below 0.15%	+/-0.3%*	
Surface flatness deviation	Below 0.15%	+/-0.4%*	
*ISO-13006:2018 UNE-EN 14411:2016			

MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11			
Breaking strength	4396 N	>1300N*	
Modulus of rupture	64.6 N/MM2	>=35N/mm2*	
Abrasion resistance	PEI 3 / 600v		
Crazing resistance	Resists 3 cycles		
*ISO-13006:2018 UNE-EN 14411:2016			

HYGIENIC FEATURES UNE-EN ISO 10545-13-14:1995		
Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance *ISO-13006:2018 UNE-EN 14411:2016	Class 5. Easy cleaning with water	3 Min.*

	SCOPE OF USE	
Technical code-1	Use on medium traffic floors	
	ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028	
Slip resistance (pendulum-wet)	CL1	
Slip resistance (ramp)	R-10	TONO 1 (C233761)*
*ISO-13006:2018 UNE-EN 14411:2016		



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

## 100337240 GENT ROBLE

## PORCELANOSA Grupo

PACKING		
Sales units per box	1.042209 M2/BOX	
Sales units per pallet	56.279312 M2/PAL	
Sales units per unit	0.347403 M2/PIECE	



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.